



SECTION VIEW

DIMENSIONS

SLAB THICKNESS (T)	DEPTH OF HOLE (D)	LENGTH OF BAR	DISTANCE FROM ℄ (d)
9"	14"	13"	6.4"
10"	16"	15"	7.1"
11"	18"	17"	7.8"
12"	19"	18"	8.6"
13"	21"	20"	9.3"

NOTES:

1. Cross-stitching to be used on longitudinal joints greater than 2" wide.
2. Holes shall be drilled on 24" centers on alternating sides of the joint. After drilling, holes shall be filled with an approved epoxy resin system then #6 (English) rebar shall be inserted.
3. Joint to be filled with epoxy mortar after cross-stitching is completed
4. All work on this detail to be paid for under the NS item labeled: Cross-stitching longitudinal joints.
5. Detail not to scale.

	<b>CROSS STITCHING LONGITUDINAL JOINTS</b>				DESIGNED CHECKED	BCT MAC	PARISH		SHEET NO. 1 OF 1
	CPR-24				DETAILED CHECKED	BCT MAC	CONTROL SECTION		
		NO.	DATE	REVISION DESCRIPTION	BY	DATE SHEET	3-03-11 1 OF 1	STATE PROJECT	